

工

Graphite Fiber Packing

ICP 925MI

Description:

Braided packing manufactured from high quality Inconel reinforced expanded graphite ribbons with a low chloride content, treated with special corrosion inhibitors. Each graphite yarn is reinforced with multi Inconel wire and jacketed with Inconel wire mesh.

Key Features:

- The inclusion of Inconel wire reinforcements ensures that the packing has excellent dimensional stability and will operate under the high stress conditions.
- Resistant to a wide range of chemicals with exception of powerful oxidizers.
- ICP 925MI offers a low coefficient of friction and high thermal conductivity.

Applications:

- High performance valve packing for high temperature and pressure application.
- Suitable for a wide range of applications such as petrochemical plants, power plants, refineries, chemical processes, steel mills, etc.



Technical Specifications:

| | P (bar / psi) | V (m / s) | T (°C Min | рН | | | |
|---|------------------|--------------|--------------|------------|--------|--|--|
| 0 | - | - | | | | | |
| | - | - | -250/ -328 | 650 / 1202 | 0 - 14 | | |
| 工 | 450 / 6525 | - | | | | | |

Availability:

ICP 925MI packing is available in the following sizes and weights:

| ion | mm | 4 | 5 | 6 | 6,4 | 8 | 10 | 11 | 12 | 12,7 | 14 | 16 | 18 | 19 | 20 | 22 | 25 |
|-----------------------|------------|-----|-------|------|------|-------|------|-------|------|------|-------|------|--------|------|--------|------|-----|
| Section | in | | 3/16" | - | 1/4" | 5/16" | 3/8" | 7/16" | | 1/2" | 9/16" | 5/8" | 11/16" | 3/4" | 13/16" | 7/8" | |
| grams per meter | [g] / [m] | 20 | 30 | 40 | 50 | 75 | 115 | 140 | 165 | 185 | 225 | 300 | 370 | 450 | 460 | 560 | 720 |
| Roll | [m] / roll | 75 | 50 | 37,5 | 30 | 33,3 | 21,7 | 17,8 | 15,2 | 13,5 | 22,2 | 16,6 | 13,5 | 11,1 | 10,9 | 8,9 | 6,9 |
| Box weight | Kg | 1,5 | | | 2,5 | | | | 5 | | | | | | | | |

CalvoSealing has a technical department at your service to provide advice and help in the correct choice of material for your specific application.

The information contained in this publication is given in good faith, with the intention of being used as a guide based on our knowledge and experience. The adequacy of the product depends on a number of specific factors for each case. Failure to take them into account can result in serious material or personnel damage. The guarantee and liability are limited to the value of the invoice of the goods supplied. CalvoSealing remains in constant development, so it reserves the right to change the product design and properties without prior notice.

